

*Laboratorium voor
Aanwending der Brandstoffen en
Warmteoverdracht*

St.-Pietersnieuwstraat 41, B - 9000 Gent
Tel. 09 264 32 88

Proefstation: Ottergemsesteenweg 711, B - 9000 Gent
Tel. 09 243 77 50 - Telefax 09 243 77 51

Beproeivingsverslag Nr 10285A
Translation

Sponsor

ONDEX
57, Avenue de Tavaux
F - 21800 CHEVIGNY - SAINT-SAUVEUR
FRANCE

Material

PVC sheet

Trade Name

TRANSLUCIDE

Name of the manufacturer

ONDEX
57, Avenue de Tavaux
F - 21800 CHEVIGNY - SAINT-SAUVEUR
FRANCE

Nature of the tests

Tests concerning the reaction to fire of this material according to the Royal decree of 7 July 1994 amended by Royal decree of 19 December 1997 and based on BS 476 - Part 7 (1997).

This report consists of

- 5 pages
- 3 annexes including
 - 1 annex with photograph
 - 1 annex with drawing

6. CONCLUSION

The test results relate only to the behaviour of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results are only valid for the specimen of the product as they have been tested. Small differences in the composition or thickness of the specimen may significantly affect the performance during the test and may therefore invalidate the test results.

In order to obtain test results which are representative for the product which is supplied or used, the conformity between the test specimen and the product should be assured. This is the role of the manufacturer and/or the supplier.

The PVC sheet ' **TRANSLUCIDE** ', as described in § 3 and under the conditions of the test, i.e. mechanically fixed on a fibre cement backing, **is classified in class A1** according to the Royal decree of 7 July 1994 – Annex 5 : reaction to fire of materials – modified by Royal decree of 19 December 1997, **and is classified in class 1**, according to the British Standard BS 476 - Part 7 – 1997.

Ghent, 07 January 2002
Translation made, 07 January 2002



ing. T. JACQUEMYN



Prof.dr.ir. P. VANDEVELDE
Director

BS 476 part 7 En nr6.doc